



Certified to ISO
9001:2015
without design

50 Years of dedicated service

2998 Eastern Road • P.O. Box 1012 • Norton, Ohio 44203
330.825.4565 • Fax 330.825.8699
WWW.ELSTONE.COM

THE FACTS

STONEKOTE®-SUPERSHINE

CONFIDENTIALITY NOTICE: These documents contain confidential information belonging to the sender, which is legally privileged. The information is intended only for the use of the individual or entity this is being sent to. If you are not the intended recipient, you are hereby notified that any disclosure, copying, distribution or the taking of any action in reliance on the contents of this information is strictly prohibited.

DESCRIPTION:

STONEKOTE®-SUPERSHINE was designed to give a non-porous fluorocarbon surface with high release characteristics, low coefficient of friction and excellent chemical resistance. Several colors are available.

USES:

The primary use of this product is for industrial end-uses which require chemical or corrosion resistance, or for those areas, which require a very high level of non-stick character. **STONEKOTE®-SUPERSHINE** exhibits melt flow behavior. If the coating is held above the flow temperature for a sufficient time, the resultant film will be non-porous. **STONEKOTE®-SUPERSHINE** is a perfluorocarbon and is inert to most substances. **STONEKOTE®-SUPERSHINE** is excellent for chemical corrosion resistance and has been extensively used as coating on chemical storage tanks, liquid transfer pipes, valve components, etc.

STONEKOTE®-SUPERSHINE also has excellent non-stick properties and is commonly used as a permanent mold release coating. **STONEKOTE®-SUPERSHINE** can be used continually at temperatures as high as 400°F (204°C) and intermittently up to 450°F (232°C) without significant thermal decomposition. It is recommended, however, that these coatings be tested when intended end-use temperature approaches these limits.

FDA STATUS:

This product conforms with regulations governing use for direct food contact.

Guarantee of performance of applied coatings by E. L. Stone Company are neither implied nor expressed. E. L. Stone Company has no control over the myriad of possible service conditions (chemicals, temperatures, mixtures, etc.) E. L. Stone Company recommends that a test sample first be evaluated by the customer under conditions as close as possible to their intended service condition.

® REGISTERED SERVICE MARK OF E.L. STONE COMPANY, INC.